

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
1 November 2001 (01.11.2001)

PCT

(10) International Publication Number
WO 01/81911 A1

(51) International Patent Classification⁷: **G01N 27/49**

(21) International Application Number: **PCT/GB01/01862**

(22) International Filing Date: **26 April 2001 (26.04.2001)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(30) Priority Data:
0010180.8 **26 April 2000 (26.04.2000)** **GB**

(71) Applicant (for all designated States except US): **CITY TECHNOLOGY LIMITED [GB/GB]**; City Technology Centre, Walton Road, Portsmouth PO6 1SZ (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **DOWNER, Anthony, Charles [GB/GB]**; 4 Westways, Bedhampton,

Havant, Hants PO9 3LN (GB). **CHAPPLES, John [GB/GB]**; 109 Woodfield Avenue, Farlington, Portsmouth, Hampshire PO6 1AW (GB). **MILLAR, Andrew, Peter [GB/GB]**; 16 Knowsley Crescent, Cosham, Portsmouth, Hants PO6 2PJ (GB).

(74) Agent: **GILL JENNINGS & EVERY**; Broadgate House, 7 Eldon Street, London EC2M 7LH (GB).


(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European

[Continued on next page]

(54) Title: **GAS SENSOR ASSEMBLY AND METHOD**

(57) Abstract: A gas sensor assembly comprises a housing (65) including a bore (61). A pin (50) extends through the bore (61) and an O-ring (100) is located in the bore. The O-ring (100) contacts the pin (50) and parts of the bore (61) so as to be restrained against movement in both lateral and axial directions. Two- and three-shot moulding processes are described for fabricating the assembly.



WO 01/81911 A1



patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report.

— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

GAS SENSOR ASSEMBLY AND METHOD

5 The invention relates to a gas sensor assembly and a method for manufacturing a seal assembly for a gas sensor assembly.

10 There are a variety of gas sensor constructions in which it is necessary to seal a member such as a pin or the like into a bore so as to prevent the passage of liquid or gas through the bore. O-rings have been used in the past to achieve such sealing both in cases where the components move relative to one another (such as described in US-A-4221651) and in which they are relatively static. The present invention is concerned with a static arrangement of components.

15 The method of securing O-rings in a static sealing configuration recommended by manufacturers is to place the ring in a U-shaped recess extending around the bore so that the ring contacts the elongate member and the seal action is based on the ability of the seal to undergo axial or radial deformation of its cross-section. In order for the seal to function properly, manufacturers require that the size of the groove or channel is larger than the O-ring cross-section typically having a cross-sectional area more than 25% that of the O-ring so that the pressure can act on a relatively large part of the ring surface and so that there is sufficient space in the groove should any volume increase of the O-ring occur due to exposure to chemicals.

We have found, however, that some leakage of liquid still occurs in these configurations.

30 In accordance with a first aspect of the present invention, a gas sensor assembly comprises a housing containing gas sensing components; a member secured to the housing; and an annular seal supported by the housing in contact with the member and parts of the housing so as to be restrained against movement in both lateral and both axial directions.

We have undergone detailed investigations into the use of annular seals such as O-rings in these static situations and we have realized that one problem that can occur in certain applications is that if the fluid pressure reduces, then the seal will relax to an extent dependent upon the elastic properties of the material. Furthermore, in certain applications such as electrochemical gas sensors, there may well be no pressure exerted by the retained liquid (the electrolyte). However, by virtue of the nature of the assembly, the joints between the mating surfaces act as capillary channels allowing the liquid to wick up into the seal area. Thus, the region around the seal quickly becomes bathed in liquid such as acid under conditions where the seal itself is not necessarily under compression. Thus, the possibility of leakage is increased.

Our solution is to ensure that the seal is restrained on all four sides and is preferably stressed or always under compression whatever the fluid pressure and thus the seal condition is maintained.

The invention can be used in a wide variety of situations in which seals against gases and/or liquids are required. It is particularly useful where the member is an electrical connector located in a bore but is also applicable to seal other components such as a gas filter top.

In addition, the invention is applicable to a wide variety of gas sensors such as electrochemical, pellistor, infrared or colorimetric gas sensors. For example, infrared devices have O-rings around their gas chambers, and colorimetric sensors with two part housings which clip together, to restrain a filter membrane via an O-ring. Pellistor housings involving O-ring seals are also known.

The invention is of particular benefit when used with an electrochemical gas sensor of the kind comprising sensing and counter electrodes and intervening electrolyte located within a housing. The electrodes are electrically

connected to respective connectors extending through bores in the housing to which they are sealed.

The connectors provide an electrical connection between (a) the internal electrode and associated current collection means and (b) the external circuit where the sensor output is measured and processed. Additionally, such connectors may be used to allow potentiostatic control of the sensor electrode operating potential via appropriate circuits. Connectors used in this application require relatively high conductivity (to limit any IR losses between the sensor and the indicating/controlling circuitry). Suitable materials include platinum and gold, often in the form of coatings on nickel or steel components, graphite (in rod form), and metal coated and/or plated polymerics.

These connector components may be in the form of, for example, pins, pads, wires, ribbons, etc.

An important aspect in the construction of these sensors is the prevention of leakage of electrolyte. This is particularly important in the case of oxygen sensors which employ liquid electrolyte, usually in the form of strongly alkaline liquid. Any minor defect in the sensor represents a potential leakage path. In particular, it is well known that the electrical connections through the housing are frequently the sources of electrolyte leakage.

In comparatively large sensors where minimisation of internal volume is not a primary design requirement, it is common to incorporate a double-walled construction method, so that the connectors pass through the sensor body in a region which is already isolated from the electrolyte reservoir. Under such circumstances, the constraints placed upon the connector/body seal, whilst significant, are relatively easily managed.

However, in sensors where internal volume is at a great premium (for example in metal-air oxygen sensors where the device lifetime is fundamentally dictated by the volume of consumable lead incorporated), it is generally

not possible to employ a double-walled method of construction. In these circumstances, the longevity and reliability of the connector/body seal are critical.

5 A typical example of a known construction makes use of a connector pin which passes through a moulded polymer sensor housing in an area containing an aggressive liquid electrolyte (which may be an acid or alkaline material). Current design and production methods usually rely on the interference fit of the connector into the housing in order
10 to provide both mechanical fixation and an hermetic seal, thereby preventing the transport or migration of electrolyte from within the sensor body (i.e. leakage).

The main shortcomings of this technique are that due to

- 15 • strain acceptance limits,
- differing coefficients of thermal expansion,
- the effect of mould processing upon the polymer characteristics, and
- ageing characteristics of the differing
20 materials involved (leading to creep),

the properties of the hermetic seal are not consistent. Therefore, leakage is generally not particularly well controlled and may cause premature cell failure and/or external contamination with electrolyte.

25 In other examples, a barb can be added to the pin to assist in its retention once the initial insertion has been made. This can be important where, for example, the pin is pushed into and removed from sockets on connector boards which might tend to withdraw the pin from the sensor
30 itself. As one increases the size of the barbs beyond that which can be readily forced through a given bore, it is also a natural step to utilize "hot insertion" processes, where thermal and/or ultrasonic methods (for example) are used to cause local heating of the sensor housing which
35 then cools and re-seals around the pin and barb. However, none of these additional steps are in themselves sufficient to guarantee leakproof seals.

Consequently, the invention is particularly suited to overcome these problems with electrochemical gas sensors.

In some cases, the annular seal is unstressed but in the preferred arrangement the seal is stressed in at least one and preferably all lateral and axial directions.

The annular seal may be made of (natural) rubber but can advantageously employ a wide range of suitably compliant materials. In various circumstances, silicones, (thermoplastic) elastomers, polymers, PTFE, soft metals etc. might all be selected on the grounds of particular properties (e.g. chemical resistance, deformability, temperature behaviour, etc.).

The seal is typically an O-ring, either of the conventional type having a circular cross-section when relaxed or a non-circular cross-section as described below.

Additional sealing may be achieved by utilizing a cured potting compound compatible with the fluid to be used, the housing and elongate member materials.

We have found that using a suitable potting material, particularly if it is thermally or optically, eg UV, curable, significantly increases the integrity of the seal. This aspect of the invention, however, is applicable to any potting compound with properties which render it physically (e.g. through thermal expansion etc) and chemically (i.e. resistant to attack, not corrosive) compatible with the liquid, elongate member and housing materials. Sealing on the outside of the housing is preferably employed, but in principle this could also (or alternatively) be done inside the housing. Although shadowing may be a problem in the case of light-cured materials, photoinitiated cationic compounds, where light is used to commence the reaction which then proceeds unaided, are now being considered for such applications. These do not suffer from significant shadowing.

In electrochemical gas sensors, the use of gelled electrolyte in place of a liquid has been proposed to further reduce the risk of electrolyte leakage. In such

cases, the electrolyte is immobilised within a suitable gelling agent in order to reduce the free liquid volume within the casing.

5 The gelling reaction may take place in situ i.e. by placing the reactants in the housing and then running the entire assembly through an appropriate thermal curing cycle. However, some ungelled liquid tends to remain within the sensor, and the whole sensor assembly is subjected to thermal stresses which are typically at the
10 extremes of the recommended operating range and may even be outside the specified operating conditions. The use of "pre-gelled" electrolyte, which is mixed with the gelling agent prior to introduction into the sensor minimizes the free liquid volume and obviates the need for thermal
15 cycling of the sensor hardware.

However, experience shows that the use of gel does not allow any compromise in the efforts taken to provide good seals in regions where the electrolyte comes into contact with members passing through the sensor body. Indeed,
20 given the requirement for equally robust seals irrespective of the presence or absence of gelling agents, sensor manufacturing processes may actually be simplified by using liquid electrolytes. All these options are open to the sensor designer.

25 Another reason why leakage can occur in seal assemblies of this type is due to the number of components involved and therefore we provide in accordance with a second aspect of the present invention, a method of manufacturing a seal assembly for a gas sensor assembly,
30 the seal assembly comprising a housing to which a member is secured in use; and an annular seal supported by the housing, the method comprising moulding the housing and seal in separate injection moulding shots, such that the seal contacts the member in use so as to seal the bore
35 against the passage of fluid.

In this aspect of the invention, instead of providing the seal as a separate component, it is pre-moulded into

the housing. Thus, the component count is being reduced which not only assists in reducing the leakage problem but also simplifies assembly. As with the first aspect of the present invention, preferably the seal is located in an annular, generally U-shaped recess opening into the housing and contacts opposed sides of the recess and the side of the recess opposite the member. The term "U-shaped" is to be read broadly and to include laterally opening recesses being a variety of cross-sections such as square, rectangular, hyperbolic, etc.

Most preferably, the seal is stressed in at least one, preferably all, lateral and axial directions.

A further advantage of this method is that the seal may be chemically bonded to the housing thus significantly improving the seal and avoiding capillary leakage. Some overall compression of the seal is generally desirable which, where the seal surrounds a bore, could be achieved by providing the seal slightly proud of the bore. However, this compression is likely to be significantly less than that required to form a conventional seal in order to provide the required integrity.

Typically, the housing is moulded before the seal. However, in an alternative approach, the seal is moulded around the member in a first shot; and the housing is moulded around the seal and member in a second shot.

Furthermore, in accordance with a third aspect of the present invention, we provide a method of manufacturing a seal assembly for a gas sensor assembly, the seal assembly comprising a housing to which a member is secured in use, and an annular seal supported by the housing, the method comprising injection moulding the housing about the seal.

For example, a sensor housing could be moulded around a free standing, annular seal.

The method can be extended when the member is elongate and sealed in a bore of the housing to a three shot process in which in a third shot an additional seal is moulded into the bore.

The same or different, usually plastics, materials may be used in each moulding shot. Typically, the seal is fabricated from a thermoplastic elastomer (TPE) while the housing is made from another polymer.

5 The use of two-shot moulding/TPEs allows the generation of a separate seal via radial compression of the TPE. The use of a three-shot moulding technique offers additional benefits by virtue of the fact that some TPEs offer favourable sealing properties to metals (e.g. a pin
10 connector) whereas others are to be preferred for use on polymer surfaces. Thus, a three-shot moulding method potentially allows a complex seal to be fabricated using a sandwich or layered structure where, in the case of an electrochemical gas sensor, the critical electrolyte seal
15 is fabricated using materials optimised for the contacting surfaces.

The moulded seal is typically in the form of an O-ring but other forms of seal may be used. Seals with a variety of more complex footprints (e.g. a car head gasket) and
20 cross-sectional forms (e.g. "lobed" O-rings or "wiping" seals) could be used.

It will be appreciated that the invention is applicable to two, three, four or more electrode electrochemical gas sensors. Furthermore, typically the
25 housing will provide controlled gas access to the sensing electrode, for example by incorporating a gas phase, Knudsen, or solid state diffusion barrier.

Some examples of electrochemical gas sensors and methods for their assembly according to the present
30 invention will now be described with reference to the accompanying drawings, in which:-

Figure 1 is an exploded view of a sensor assembly;

Figure 2 is a cross-section through part of the housing of the sensor shown in Figure 1;

35 Figures 3A-3D are partial, perspective views of different stages in the fabrication of part of a gas sensor using a two-shot injection moulding process;

Figures 4A-4D are perspective views of part of another example of an electrochemical gas sensor housing during its fabrication using a two-shot injection moulding process;

Figures 5A-5D are perspective views illustrating the fabrication of part of a further example of an electrochemical gas sensor using a three-shot injection moulding process; and,

Figure 6 illustrates cross-sections through four alternative annular seals.

Figure 1 illustrates the primary components of a sensor assembly including a main housing component 65 which, following assembly, is bonded by welding or the like to a top housing component 2. The top housing component includes a central capillary hole 4 extending through it (which forms a gas phase diffusion barrier), a filter 5 being located in alignment with the hole 4. A sensing electrode 6 is located below the capillary hole 4. Below the sensing electrode 6 is a separator 7 and an O-ring 8. A counter electrode in the form of a lead anode 9 is positioned beneath the O-ring 8 and sits on a floor seal 10. It will be appreciated that several components have been omitted from Figure 1 for clarity and indeed the construction of the assembly shown in Figure 1 is conventional apart from the pin mountings which are to be described below.

The sensing electrode 6 and the counter electrode 9 are each connected to respective conductors (not shown) which are in turn connected to respective pins 50 which protrude through holes 61 in the base of the housing component 65. As will be described in more detail below, the pins 50 are secured in the holes 61 partly by a friction fit and partly by epoxy potting material 20. They are also sealed to the holes 61 via O-rings 100.

A dummy pin 40 extends from the base of the housing component 65 to assist in locating the sensor on a support member.

Figure 2 illustrates an example of the invention in which a T-shaped connector pin 50 is secured in a widened part 60 of the bore 61 extending through the base of the housing component 65. This securement is achieved partly by means of an interference fit between a lateral flange 62 integrally formed with the rest of the pin 50 with the surface of the bore 60 and partly by means of a potting material 20 which fills part of the space within the widened part of the bore 60. After inserting the pin 50 into the bore 61, the widened part of the bore 60 is filled with the potting material, such as an epoxy, which is then cured under UV radiation.

The electrolyte reservoir 66 defined by the housing part 65 is then provided with a consumable lead anode 67 which is saturated in electrolyte. This could be in liquid form, in which case it will be largely wicked into the compressed body of the lead wool ball by capillary action but with the possibility of some seepage of liquid. Alternatively, the electrolyte might be either pre- or post-gelled, in which case it would be more robustly held within the cavities formed by the intertwined strands of lead wool. The pre-gelled electrolyte is a liquid electrolyte with suitable additives that cause the material to "gel" by application of heat, thus reducing the amount of free liquid by a significant degree. The electrolyte is "gelled" in the lead anode 9 prior to assembly of the anode into the sensor to minimise both heat cycle stresses on the sensor, and the free liquid electrolyte inside the sensors.

The polymer preferably, although not exclusively, comprises units derived from polyacrylamides as is known in the art.

Primary leakage control is achieved by sealing the pins 50 to the housing by means of O-rings. As can be seen in the example of Figure 2 the internal end of each pin 50 is surrounded by an O-ring 100.

The O-ring 100 is made of rubber and as can be seen in Figure 2 is compressed in both lateral and axial

directions. Axial constraint is provided by an axially facing shoulder 70 of the widened part 61 of the bore 60 and by an axially upwardly facing surface 71 of the flange 62. Lateral constraint is provided by a laterally outwardly facing surface 72 of the pin 50 and a laterally inwardly facing surface 73 of the widened part of the bore 60.

The unconstrained and unstressed form of the O-ring is shown in dotted lines in Figure 2. It can be seen, therefore, that the O-ring is stressed and consequently leakage of electrolyte through the bore 61 is minimized even with variations in temperature and liquid pressure and other physical conditions since the O-ring remains in its stressed condition. The exact position of the O-ring can be varied and for example it could be located downstream of the interference fit as opposed to upstream as shown in Figure 2.

In the Figure 2 example, the various components forming the seal assembly are separately manufactured and then connected together.

We have found that significant advantages can be achieved using a two-shot or three-shot injection moulding process.

Figure 3A illustrates part of a main housing moulding 120 similar to the housing 65 in Figure 1. The housing moulding 120 is formed in a single injection moulding shot and includes a base 125, a dummy pin 40 and a bore 130 having a narrow section 131 and a widened section 132. The bore 130 can be seen more clearly in Figure 3B.

In a second injection moulding shot, a thermoplastic O-ring 135 is located in the base of the widened part 132 of the bore 130 to which it is both mechanically and chemically bonded (Figure 3C). This produces a semi-constrained form of the seal which becomes fully constrained upon the introduction of a metal pin 140 (Figure 3D) generating a seal between the pin and main

polymer housing. The pin 140 is retained in position by a radial barb 145 as in the Figure 2 example.

Figure 4 illustrates an advantageous development of the Figure 3 example. In this case, the bore 130 includes
5 a radial flange 150 produced during the first moulding shot (Figure 4A), the flange 150 having a central opening 155. In a second shot, a seal 135 is injected into the space defined between the flange 150 and the base 160 of the widened part 132 of the bore 130. In this design, the seal
10 135 is pre-constrained by this space into which it is moulded, again achieving both mechanical and chemical bonding to the base housing polymer. This means that the pin will always be fitted (Figures 4C and 4D) to a defined position therefore reducing the degree of variability in
15 seal compression. In effect, the space in which the seal 135 is located defines a U-shaped recess surrounding the bore.

Figure 5 illustrates a further development of the moulding process in which a three-shot process is used.
20 Initially, a metal pin 140 is provided (Figure 5A) as in the previous examples. This is loaded into mould tooling (not shown) and then in a first shot, a seal 160 is moulded around a flange 144 defining the barb 145 (Figure 5B).

In a second shot (Figure 5C), the main body of the
25 housing 120 is injection moulded about the pin and seal thus defining the bore 130.

Finally, in a third shot (Figure 5D), an external seal is moulded as shown at 170.

A variety of materials may be used for the different
30 components providing they are compatible with each other and Table 1 below provides a list of thermoplastic materials and an indication of where they are compatible for good adhesion.

Typically, the housing 120 will be moulded from a
35 polymer plastics material such as ABS while the seals 160,170 will be formed from thermoplastic elastomer

materials (TPEs) or high flow polymers of which suitable examples are set out in Table 1.

It will be appreciated that the Figure 4 example could be modified such that in the first shot the seal 135 is
5 moulded around the pin 140 and then the housing 120 is moulded around the seal in a similar way to the steps illustrated in Figures 5A-5C.

The two- and three-shot moulding processes are preferably carried out using a single tool although this is
10 not essential.

Whilst the designs discussed above relate to the manufacture of an oxygen sensor, the design is not limited to sealing in the region of current collectors. Neither is it limited to oxygen sensors, but can also be used to
15 generate the seals within any other areas of the gas sensor including toxic sensors, and indeed wherever an O-ring is currently employed.

In addition, although the examples described above make use of conventional O-rings with circular cross-
20 sections, a variety of other annular seals could be used. Figure 6 illustrates cross-sections through four such examples which illustrate the wide variety of cross-sections applicable.

Table 1: Typical material adhesion combinations

Material		Thermoplastics																							Rigid/flexible bonds								
																									TPE	Elastomers							
Thermoplastics	Premolding	ABS	ASA	CA	EVA	PA 6	PA 66	PC	PE-HD	PE-LD	PMMA	POM	PP	PPO MOD	OPS-GP	OPS-HI	PBTP	TPU	PVC-W	SAN	QTPR	PETP	PEI	PSU	BLEND PC-PBTP	BLEND PC-ABS	SEBS	TPU	PP/EPDM	EPDM	NR	SBR	LSR
	ABS	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	ASA	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	CA	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	EVA	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PA 6	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PA 66	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PC	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PE-HD	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PE-LD	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PMMA	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	POM	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PP	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PPO MOD	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PPO MOD GTX	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PS-HI	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PBTP	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	TPU	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PVC-W	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	SAN	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	TPR	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PETP	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PEI	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	PSU	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	BLEND PC-PBTP	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
	BLEND PC-ABS	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+	+
TPE	PP/EPDM																																
Elastomer	EPDM																																
	NR																																
	SBR																																
	LSR																																

+ Good adhesion
 o Bad adhesion
 - No adhesion

CLAIMS

1. A gas sensor assembly comprising a housing containing gas sensing components; a member secured to the housing;
5 and an annular seal supported by the housing in contact with the member and parts of the housing so as to be restrained against movement in both lateral and both axial directions.
2. An assembly according to claim 1, wherein the annular
10 seal comprising an O-ring.
3. An assembly according to claim 1, wherein the housing includes an annular, generally U-shaped recess, the annular seal being located in the recess and contacting opposed sides of the recess, the member, and the side of the recess
15 opposite the member so as to seal against the passage of fluid.
4. An assembly according to claim 3, wherein the opposed sides of the recess are substantially parallel and orthogonal to the side opposite the member.
- 20 5. An assembly according to any of the preceding claims, wherein the annular seal is stressed in at least one of the lateral and axial directions.
6. An assembly according to any of the preceding claims, wherein the annular seal is made of a plastics material.
- 25 7. An assembly according to claim 6, wherein the annular seal is bonded to the housing.
8. An assembly according to any of the preceding claims, wherein the member is additionally sealed to the housing by a cured potting compound compatible with the fluid to be
30 used, the housing and the member materials.
9. An assembly according to claim 8, wherein the potting compound is thermally or optically, e.g. UV, curable.
10. An assembly according to claim 8 or claim 9, wherein the potting compound is provided in an outwardly facing
35 opening surrounding the member.
11. An assembly according to any of the preceding claims, wherein the member is elongate and includes a laterally

extending flange, the member extending through a bore in the housing, and an annular seal contacting a surface of the flange and an adjacent elongate portion of the member.

12. An assembly according to any of the preceding claims, wherein the member comprises an electrically conductive pin.

13. An assembly according to any of the preceding claims, wherein the member is an electrical connector.

14. An assembly according to any of the preceding claims, wherein the gas sensing components define one of an electrochemical, pellistor, infrared or colorimetric gas sensor.

15. An assembly according to claim 14, wherein the gas sensing components define an electrochemical gas sensor and include sensing and counter electrodes and an intervening electrolyte located in the housing.

16. A sensor according to claim 15, further comprising means for controlling gas access to the sensing electrode.

17. A sensor according to claim 16, wherein the gas access control means comprises a gas phase, Knudsen or solid state diffusion barrier.

18. A method of manufacturing a seal assembly for a gas sensor assembly, the seal assembly comprising a housing to which a member is secured in use; and an annular seal supported by the housing, the method comprising moulding the housing and seal in separate injection moulding shots, such that the seal contacts the member in use so as to seal the bore against the passage of fluid.

19. A method according to claim 18, wherein the housing is moulded before the seal.

20. A method according to claim 18, wherein the seal is moulded around the member in a first shot; and the housing is moulded around the seal and member in a second shot.

21. A method of manufacturing a seal assembly for a gas sensor assembly, the seal assembly comprising a housing to which a member is secured in use; and an annular seal

supported by the housing, the method comprising injection moulding the housing about the seal.

22. A method according to any of claims 18 to 21, further comprising securing a member to the housing in sealing
5 contact with the seal.

23. A method according to any of claims 18 to 22, wherein the seal comprises an O-ring.

24. A method according to any of claims 18 to 23, wherein the seal contacts parts of the housing and the member so as
10 to be restrained against movement in both lateral and both axial directions.

25. A method according to claim 24, wherein the seal is stressed in at least one of the lateral and axial directions.

15 26. A method according to any of claims 18 to 25, wherein the seal is located in an annular, generally U-shaped recess opening into the housing and contacts opposed sides of the recess and the side of the recess opposite the member.

20 27. A method according to claim 26, wherein the opposed sides of the recess are substantially parallel and orthogonal to the side of the recess opposite the member.

28. A method according to any of claims 18 to 27, wherein the material of the housing is different from the material
25 of the seal.

29. A method according to any of claims 18 to 28, wherein the seal is chemically bonded to the housing.

30. A method according to any of claims 18 to 29, wherein the member is elongate and sealed in a bore of the housing,
30 further comprising moulding an additional seal into the bore in a third shot.

31. A method according to any of claims 18 to 30, wherein the member comprises an electrically conductive pin.


32. A method of manufacturing a gas sensor assembly
35 comprising manufacturing a seal assembly having at least two electrically conductive pins by a method according to

claim 31; and providing gas sensor components in the housing in electrical contact with the pins.

33. A method according to claim 32, wherein the components include sensing and counter electrodes, an intervening electrolyte located within the housing, and a gas access control member secured to the housing.
- 5


1/5

Fig.1.



2/5

Fig.2.



3/5

Fig.3A.




Fig.3B.




Fig.3C.




Fig.3D.




Fig.4A.





Fig.4B.



4/5

Fig.4C.




Fig.4D.




Fig.5A.





Fig.5B.



5/5

Fig.5C.




Fig.5D.





Fig.6.



INTERNATIONAL SEARCH REPORT

Inter national Application No

PCT/GB 01/01862

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 G01N27/49

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 G01N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 239 297 A (LAND COMBUSTION LTD) 30 September 1987 (1987-09-30) column 2, line 44 - line 53; figure 1	1-3,6, 11-18, 21-24, 26-28, 31-33
A	US 3 997 419 A (SCOTT TIMOTHY F ET AL) 14 December 1976 (1976-12-14) column 5, line 52 - line 58; figures 6,7	1,8
A	US 3 902 970 A (LEVIN HERMAN W) 2 September 1975 (1975-09-02) column 5, line 10 - line 24; figure 2 -/-	1

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

A document defining the general state of the art which is not considered to be of particular relevance

E earlier document but published on or after the international filing date

L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

O document referring to an oral disclosure, use, exhibition or other means

P document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

Z document member of the same patent family

Date of the actual completion of the international search

8 October 2001

Date of mailing of the international search report

16/10/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Duchatellier, M

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 01/01862

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 914 019 A (DODGSON JOHN ROBERT ET AL) 22 June 1999 (1999-06-22) column 4, line 66 -column 5, line 50; figure 1	1,8
A	US 5 702 576 A (KIESELE HERBERT ET AL) 30 December 1997 (1997-12-30) abstract	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intel
nel Application No
PCT/GB 01/01862

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0239297	A	30-09-1987	EP 0239297 A2	30-09-1987
			JP 62242850 A	23-10-1987
US 3997419	A	14-12-1976	NONE	
US 3902970	A	02-09-1975	AU 7165374 A	29-01-1976
			CA 1007701 A1	29-03-1977
			CH 589288 A5	30-06-1977
			DE 2436670 A1	20-02-1975
			FR 2239684 A1	28-02-1975
			GB 1440540 A	23-06-1976
			IT 1025030 B	10-08-1978
			JP 961034 C	28-06-1979
			JP 50072689 A	16-06-1975
			JP 53037234 B	07-10-1978
US 5914019	A	22-06-1999	AU 3812695 A	31-05-1996
			CA 2204413 A1	17-05-1996
			CN 1162357 A ,B	15-10-1997
			DE 69514943 D1	09-03-2000
			DE 69514943 T2	05-10-2000
			EP 0871874 A1	21-10-1998
			ES 2144148 T3	01-06-2000
			FI 971846 A	02-06-1997
			WO 9614576 A1	17-05-1996
			JP 10508696 T	25-08-1998
			RU 2147120 C1	27-03-2000
			DK 871874 T3	26-06-2000
US 5702576	A	30-12-1997	DE 19514214 A1	24-10-1996
			FR 2733052 A1	18-10-1996
			GB 2299863 A ,B	16-10-1996

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☒ BLACK BORDERS

☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

☐ FADED TEXT OR DRAWING

☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING

☐ SKEWED/SLANTED IMAGES

☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS

☐ GRAY SCALE DOCUMENTS

☐ LINES OR MARKS ON ORIGINAL DOCUMENT

☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.